

Nifty PRODUCTS

P.O. Box 161, Marlboro, NJ 07746-0161
4 Jocama Boulevard, Old Bridge, NJ 08857-9743
732-591-1140 800-631-2172
FAX: 732-591-8477

NIFTY'S T3NA3 NON-ASPHALTIC, 3-WAY REINFORCED TAPE

The paper used is made from two sheets 100% unbleached or semi-bleached virgin chemical wood pulp with a basis weight, prior to gumming, of 25# on the top sheet and 25# on the bottom sheet. The adhesive used is synthetic, starch-fortified, non-toxic, and odorless. Glass fibers are used for reinforcing and are spaced not more than an average of 5/8" apart in the machine direction and are arranged in a diamond pattern in the cross machine direction with the spacing between the parallel sides of the diamond averaging not more than 1". The laminating material is non-asphaltic, water-resistant, flexible, and non-staining amorphous polypropylene. The tensile strength is 61 lbs/inch width in the machine direction and 31 lbs/inch width in the cross machine direction.